LG Hausys sign & graphic materials

LC5110/5111/5120/5121

Metalized Film Series

Description

Metalized Film is an opaque polyester film. It offers exceptional metallic effect and has excellent cutting properties on a wide range of computerized cutting plotter.

Features

- Excellent pearlescent effect
- High gloss surface/Brushed surface
- Color range (Silver/Gold)
- Excellent weather resistance: Solvent based acrylic adhesive
- Select liner: Double side olefin coated Paper

Characteristics

| Item | Description | |
|----------------------|--|--|
| Film | 2.0 mils(0.05mm) opaque film with gloss finish | |
| Film thickness | 3.1 mils(0.08mm)with adhesive (± 10%) | |
| Adhesive | Acrylic based pressure sensitive (Solvent based) | |
| Adhesive color | Clear | |
| Liner | Double side olefin coated Paper / kraft Paper | |
| Application Surfaces | Flat, rigid surface | |
| Application Temp | $\geq 10^{\circ}$ C (18 to 25 °C optimum) | |

Converting Methods

Cutting

Use one of these cutting methods

Electro cut/Hand cut/Kiss cut/Die cut

⇒ These factors can affect cutting and weeding quality

Weight on the knife: Slightly notch the liner.

Sharpness of the knife blade: Dull knifes creates a serrated look to cut edge of the film



Update: 2013-02-01

LG Hausys sign & graphic materials

Compatible Products

- LG Banner/FLEX products
- LG Application Tape (LC2000)

Physical Properties

| Property | Specification | Test Method |
|--------------------------------|-----------------------|---|
| Thickness (Including adhesive) | 3.1mils(80\mum) ± 10% | Micrometer |
| Tensile strength | ≥ 3kg/cm | ASTM 882 |
| Elongation | ≥ 50% | ASTM 882 |
| Peel adhesion(24hrs) | ≥ 1,600g/in | 180 peeling PSTC-1 |
| Service temp. range | -25℃ ~82℃ | Film applied Al panels 24hrs prior test |
| Application temp. | ≥ 10 °C | 18 to 25 $^{\circ}$ C optimum, on clean substrate |

Durability

Durability is based on field experience and exposure tests in South Korea. Outdoor durability is 1 year, when properly processed and applied (unprinted film vertical exposure).

Shelf Life

Shelf life is 1 year from factory shipment.

Storage condition: Free from excessive moisture, temperature, direct sunlight (20 °C x 50% R.H)

Notice:

The information provided on this sheet represents typical properties and does not constitute a specification. No liability will be accepted for errors and omissions and in no circumstances shall LG Hausys Ltd be liable for any loss or injury arising directly or as a consequence of the publication of this data sheet. All LG Hausys vinyl sold are subject to our conditions of sale. LG Hausys also retains the right to make changes in sizes and specifications of products without prior notice.



Update: 2013-02-01